

## **ABSTRACT OF THE DISCLOSURE**

A method for producing a hydrocyanic acid synthesis catalyst is disclosed which comprises sequential exposure of an iron surface, such as, for example, pig iron, to sequential oxidative and reductive atmospheres, preferably using repetitive cycles, the oxidative atmosphere preferably containing 5% to 3% by volume oxygen and the reductive atmosphere preferably containing 1% to 99% hydrogen.

M:\DOC\PAT\GRC\205701\_APP.DOC

卷之三